

AL

**POLYPROPYLENE RESIN COMPOSITION**

Patent Number: JP10036589  
Publication date: 1998-02-10  
Inventor(s): MAEDA SHIGENORI; OTANI TAKANORI; ABE MASARU; ASANUMA TADASHI  
Applicant(s):: MITSUI PETROCHEM IND LTD  
Requested Patent: ☐ JP10036589  
Application Number: JP19960189168 19960718  
Priority Number(s):  
IPC Classification: C08L23/12 ; C08K5/098 ; C08L53/00  
EC Classification:  
Equivalents:

**Abstract**

**PROBLEM TO BE SOLVED:** To obtain a polypropylene resin composition from which chlorine and alkali metal components are not extracted even by extracting the formed material by water, and capable of being suitably used for a package of an electronic part or an electronic material extremely prohibited from a halogen compound or an alkali metal compound such as a silicon wafer.

**SOLUTION:** This polypropylene resin composition is obtained by adding 10-10000ppm an alkaline earth metal salt of a higher aliphatic carboxylic acid to a polypropylene resin containing  $\leq 5$ ppm chlorine content and consisting of a propylene homopolymer having  $\geq 0.930$  mesopentad ratio or a block copolymer of propylene having a homopolymer part of propylene having  $\geq 0.930$  mesopentad ratio with ethylene.

Data supplied from the esp@cenet database - I2